


**2 ENTRIES**
**3 ENTRIES**
**4 ENTRIES**
**5 ENTRIES**
**MULTI-ENTRY SEALS**

Ref.	Suitable for		n° entries	Ø Dia entry (mm)	Quantity Box/Bag
	<b>MAXIblock®</b>	<b>MAXIbrass®</b> <b>MAXIinox</b>			
36A3M1623	M16 + Pg11	M16 + Pg11	2	3	1.500/100
36A3M1624	M16 + Pg11	M16 + Pg11	2	4	1.000/100
36A3M16322	M16 + Pg11	M16 + Pg11	3	2,2	1.500/100
36A3M2025	M20 + Pg13,5	M20 + Pg13,5 + Pg16	2	5	500/100
36A3M2034	M20 + Pg13,5	M20 + Pg13,5 + Pg16	3	4	500/100
36A3M20356	M20 + Pg13,5	M20 + Pg13,5 + Pg16	3	5,6	500/100
36A3M2526	M25	M25 + Pg21	2	6	300/50
36A3M2536	M25	M25 + Pg21	3	6	300/50
36A3M2537	M25	M25 + Pg21	3	7	300/50
36A3M2545	M25	M25 + Pg21	4	5	300/50
36A3M2546	M25	M25 + Pg21	4	6	300/50
36A3M2554	M25	M25 + Pg21	5	4	300/50
36A3M3228	M32	M32	2	8	150/50
36A3M3239	M32	M32	3	9	150/50
36A3M32465	M32	M32	4	6,5	150/50
36A3M3248	M32	M32	4	8	150/50
36A3M4078	M40	M40	7	8	100/100
36A3M40106	M40	M40	10	6	100/100
36A3M5088	M50 + Pg 36	M50 + Pg 36	8	8	50/50
36C201629	Pg16	-	2	3+9	400/50

**Technical features:**

MATERIAL  
 HARDNESS  
 DENSITY  
 BREAKING RESISTANCE  
 BREAKING ELONGATION  
 TEARING  
 OPERATING TEMPERATURE

COMPRESSION SET (24 hours at 100°C sch.25%) ASTM D 395 B

**Reference Norm:**

ASTM D 2240  
 ASTM D 1817  
 ASTM D 412  
 ASTM D 412  
 ASTM D 624

NEOPRENE® (CR) rubber  
 70 SHORE A  
 1,358 gr/cm<sup>3</sup>  
 15 N/mm<sup>2</sup> (Mpa)  
 300%  
 25 N/mm  
 -40°C ÷ +120°C (continuous)  
 +130°C (short periods)  
 19%

**Chemical and physical resistance of the material:**

FUEL and PETROL - critical  
 GREASES and VEGETABLE OILS - sufficient  
 LIQUID PARAFFIN - sufficient  
 TURPENTINE - critical  
 DILUTED ACIDS - not critical  
 CHLORINE - not critical  
 NORMALLY CHLORINATED WATER - not critical  
 SEA WATER - not critical  
 DILUTED ALKALI - not critical  
 AGING - not critical  
 OZONE 70 hours with elongation of 10% at 38°C ozone 50 pphm

**Cembre SpA**

Via Serenissima, 9 - 25135 Brescia (Italy)  
 Tel.: +39 030 36921 - Fax: +39 030 3365766  
 Web: www.cembre.com - Email: info@cembre.com